

PATENT APPLICATION

MAGNESIUM AMMONIUM PHOSPHATE CEMENT COMPOSITION

Inventors: MICHAEL ZIMMERMANN, a citizen of Germany,
residing at Zehnthofgasse 10,
D-65931 Frankfurt am Main
GERMANY

Assignee: Kyphon Inc.
1350 Bordeaux Drive,
Sunnyvale, California 94089

Status: Small Entity

MAGNESIUM AMMONIUM PHOSPHATE CEMENT COMPOSITION**CROSS-REFERENCES TO RELATED APPLICATIONS**

[0001] This application is a continuation of application no. 10/070,670 (Attorney Docket No. 019433-000610US), filed on March 4, 2002, which was a 371 National Phase of PCT/EP01/07605, (Attorney Docket No. 019433-000610PC) filed on July 3, 2001, which claimed priority from DE 100 32 220.4, (Attorney Docket No. 019433-000600DE), filed on July 3, 2000, the full disclosures of which are incorporated herein by reference.

BACKGROUND OF THE INVENTION

[0002] 1. Field of the Invention. The invention relates to a magnesium ammonium phosphate cement preparation, a process for its production and an associated use.

[0003] This invention relates in particular to a biologically degradable cement, which consists *in its main phase* of magnesium ammonium phosphates and nanoapatites after hardening and thus at the same time has a high strength.

[0004] The material may be used as bone replacement, for bone augmentation and for bone regeneration.

[0005] It may serve as excipient for pharmaceutical or biological active ingredients.

[0006] The most important mineral constituents in human bone and tooth enamel are calcium and phosphate. However, considerable quantities of sodium, magnesium and carbonate are also present.

[0007] It is known from precipitation studies of synthetic systems that sodium ions and carbonate ions may be incorporated very easily into calcium phosphate precipitates resulting in a molecular structure similar to apatite.

[0008] However, magnesium has a strong tendency to precipitate in a different structure not similar to apatite.

[0009] Calcium phosphate precipitated physiologically as bone and dentine is nanocrystalline. It cannot be seen from an X-ray diffractogram, due to line broadening, whether it is apatite or other structures.

[0010] Some scientists are of the opinion that so much magnesium occurs in bone and dentine that this cannot all be taken up in the apatite structure. Therefore, a mixed form of the mineral of nanoapatite and nanodolomite or nanostruvite is assumed here.

[0011] Calcium phosphates are not only biocompatible but are recognized by the living cell as belonging-to-the-body. Therefore, there are many biomaterials and medical products which consist partly of calcium phosphate.

[0012] Calcium phosphate ceramics have been on the market since about 1970, partly in the form of prefabricated blocks or as granules.

[0013] Implantations of these materials in bone structures are predominantly successful.

[0014] The biggest disadvantage of these systems is that the blocks have to be prefabricated and the granules drift away (flood out) from the side of the implantation. This often leads to failure of such implantations.

[0015] Calcium phosphate ceramics are most successful when they consist of hydroxyl-apatite (HA) or of beta-tertiary calcium phosphate (β -TCP, a whitlockite-like structure) or when the calcium phosphate ceramics consist of both, HA and β -TCP in variable ratios. HA is virtually non-resorbable from bone implantations, whereas β -TCP is slowly resorbed and replaced by new bone.

[0016] It is therefore possible to influence the degree of resorption of calcium phosphate ceramic by changing the β -TCP/HA ratio.

[0017] It is likewise possible to admix other resorbable materials, such as: monetite CaHPO_4 , brushite $\text{CaHPO}_4 \cdot 2\text{H}_2\text{O}$, calcite CaCO_3 and dolomite $\text{CaMg}(\text{CO}_3)_2$.

[0018] Since 1985 attempts have been made to develop calcium phosphate cements in order to avoid the disadvantages of prefabricated or granular-like calcium phosphate ceramics (W.E. Brown and L.C. Chow, "A new calcium phosphate, water-setting cement", Cem. Res. Prog. 1986 352-379 (1987)).

[0019] This includes a brushite cement not yet commercially available having a Ca/P molar ratio of the precipitated phase of 1.00. This phase is not nanocrystalline but microcrystalline.

[0020] All the other calcium phosphate cements developed hitherto have a nanocrystalline precipitation structure and a Ca/P molar ratio of ≥ 1.5 , which may be further increased by addition of carbonate. These materials are known under United States 5 605 713; European

application 0 835 668; World 96/14265, and some of these materials are already on the market.

[0021] There are contradictory reports regarding the resorbability of these materials after implantations in bone and soft tissue.

- 5 [0022] In each case, calcium phosphate cements based on hydroxylapatite (HA) which are not resorbable (HA ceramics see above) and calcium phosphate cements based on deficient calcium hydroxylapatites (CDHA, calcium deficient hydroxylapatites) which are good osteotransductively, are differentiated.

- 10 [0023] This means for the last-mentioned case, that they may be resorbed by osteoclasts and may be replaced by new bone tissue from osteoblasts.

[0024] Resorption of these cements depends crucially on the local bone transformation mechanisms.

- 15 [0025] Today, most surgeons require a calcium phosphate cement, in which initially a mechanically supporting mode of action is brought to bear, but the final resorption lags behind independently of the local transformation mechanisms of the bone, that is that the material is completely degraded. In addition, it is known in orthopaedics that vital bone only remains where it is required from the biomechanical point of view. This is known as the so-called Wolff's Law. Consequently, if a calcium phosphate cement introduced into a bone defect has a higher compressive strength than the bone surrounding it and this high
20 compressive strength remains unchanged, this leads to degradation of bone tissue lying around the implant (here calcium phosphate cement).

- [0026] In order to fulfill this requirement, even if only partly, some manufacturers have admixed substances into their CDHA cements which are similar to nanoapatite, which are passively resorbed by the bodily fluids due to the concentration gradients, such as for
25 example monetite (CaHPO_4) or calcite (CaCO_3) as known from European 0 543 765.

[0027] However, this only partly solves the problem. A cement is also required which can be resorbed completely passively and in which the resorption front and the deposition front are in direct contact.

- 30 [0028] Gypsum for example does not fulfill this requirement. Gypsum is resorbed so rapidly that there is always a gaping hole between the resorption front and the deposition

front and these materials do not have adequate supporting function due to their low resistance to pressure. Such materials are disclosed, for example under United States 5 281 265.

[0029] For these reasons, it is desirable to provide a bone replacement material, which initially takes over the lost supporting function of the bone with high resistance to pressure, but then successively decreases in resistance to pressure, as a result of which the endogenous bone transformation processes (remodeling) are stimulated and hence more rapid osteoneogenesis and hence also active resorption of the bone replacement material is introduced. This may also be achieved by incorporating a slightly soluble substance, for example into a hardening cement paste. Because bone grows well into macroporous structures, it is advantageous to admix granular or pellet-like, solubilizing substances consisting of, for example sugars, salts (for example NaCl) or gypsum (CaSO_4) into the cement paste. They are then leached out very rapidly in the body from the hardened cement structure and a porous sponge-like structure remains. Production of a porous (finished) cement outside the body is also conceivable.

[0030] In order to be able to use a cement for dental applications, such as for example filling and sealing of small dentine channels, filling of tooth cavities after vital extirpation, utilizing such a cement as sub-filling material in endodontology, such a material may not shrink to prevent passage of bacteria. Even a material having low-grade expandable properties would be desirable.

[0031] It is the object of the invention to provide a cement preparation, with which the disadvantages of the state of the art are avoided.

BRIEF SUMMARY OF THE INVENTION

[0032] The present invention provides a magnesium ammonium phosphate cement preparation, comprising: a powder mixture having molar quantities of the components calcium (Ca), magnesium (Mg) and orthophosphate (P) in the mixture in the ranges $1.00 < \text{Ca/P} < 1.50$ and $0 < \text{Mg/P} < 0.50$; an ammonium salt; and water and/or an aqueous solution.

[0033] In one embodiment, the present invention provides a magnesium ammonium phosphate cement preparation, comprising: a powder mixture, consisting of (α -TCP, β -TCP, $\text{MgHPO}_4 \times 3 \text{H}_2\text{O}$, KH_2PO_4 and Na_2HPO_4 ; an ammonium salt; and water and/or an aqueous solution.

[0034] In another embodiment, the present invention provides a magnesium ammonium phosphate cement preparation, comprising: a powder mixture consisting of: α/β -TCP, $\text{MgHPO}_4 \times 3\text{H}_2\text{O}$, KH_2PO_4 , Na_2HPO_4 and $\text{Mg}_3(\text{PO}_4)_2$; and an aqueous solution containing ammonium ions.

5 [0035] In a further embodiment, the present invention provides a magnesium ammonium phosphate cement preparation, comprising: a powder mixture consisting of: α/β -TCP, $\text{MgHPO}_4 \times 3\text{H}_2\text{O}$, KH_2PO_4 , Na_2HPO_4 and $\text{Mg}_3(\text{PO}_4)_2$; and an aqueous solution containing ammonium ions.

10 [0036] In yet another embodiment, the present invention provides a magnesium ammonium phosphate cement preparation, comprising: a powder mixture consisting of: α/β -TCP, $\text{MgHPO}_4 \times 3\text{H}_2\text{O}$, KH_2PO_4 , Na_2HPO_4 and $\text{Mg}_3(\text{PO}_4)_2$; and an aqueous solution containing ammonium ions.

[0037] The preparations of the present invention can also include one or more of the following features:

15 the aqueous solution is an aqueous solution of an ammonium salt having a pH value in the range from $7 < \text{pH} < 12$;

the ammonium salt is present in the powder mixture and the molar quantities of the components calcium (Ca), magnesium (Mg), orthophosphate (P) and ammonium (NH_4) lie in the ranges $1.00 < \text{Ca/P} < 1.50$ and $0 < \text{Mg/P} < 0.50$ and $0 < \text{NH}_4 < 0.50$;

20 the powder mixture comprises α/β -tertiary calcium phosphate (α/β -TCP) and preferably $\text{MgHPO}_4 \times 3 \text{H}_2\text{O}$;

the powder mixture, apart from α/β -TCP and $\text{MgHPO}_4 \times 3\text{H}_2\text{O}$, additionally contains $\text{Mg}_3(\text{PO}_4)_2$;

the aqueous solution comprises an aqueous $(\text{NH}_4)_2\text{SO}_4$ solution;

25 the powder mixture comprises $(\text{NH}_4)_2\text{SO}_4$;

a mixing liquid consists of an aqueous $(\text{NH}_4)_2\text{HPO}_4$ solution;

the powder mixture additionally comprises KH_2PO_4 ;

the powder mixture additionally comprises Na_2HPO_4 ;

additionally SrCO_3 ;

the level of SrCO_3 is 0.01 to 10 wt. %, preferably 0.1 to 5 wt.%, based on the total weight of the preparation;

5 an aqueous solution of an ammonium salt as mixing liquid;

an aqueous solution of a magnesium salt as mixing liquid;

as additional component, ZnO in the powder mixture and/or in the mixing liquid;

the powder mixture additionally contains $\text{Ca}_2\text{NaK}(\text{PO}_4)_2$ and/or CaKPO_4 ;

10 as an additional component, fluoride ions in the powder mixture and/or in the mixing liquid; and

as additional components, pharmaceutical and/or bioactive active ingredients in the powder mixture and/or in the mixing liquid, preferably antibiotics, cytostatic agents, analgesics, disinfectants, growth factors, proteins or elastin inhibitors in therapeutic doses.

15 **[0038]** The invention also provides a process for producing a magnesium ammonium phosphate cement wherein the powder mixture is mixed with the mixing liquid while achieving uniform distribution of the liquid in the powder mixture and the paste thus obtained is applied on or to the target zone or is introduced into the target zone and is allowed to harden, wherein the components react such that the cement formed has microcrystalline
20 magnesium ammonium phosphate.

[0039] In another embodiment, the invention provides a process for producing a magnesium ammonium phosphate cement using a magnesium ammonium cement preparation, in which the powder mixture is mixed with the mixing liquid while achieving uniform distribution of the liquid in the powder mixture and the paste thus obtained is applied
25 on or to the target zone or is introduced into the target zone and is allowed to harden with formation of cement containing microcrystalline magnesium ammonium phosphate.

[0040] The process in accord with the present invention also can include one or more of the following features:

granular, thus granular particles which are slightly soluble in aqueous liquids, between about 10 μm and about 300 μm , preferably between 50 μm and 200 μm , are added to the powder mixture; and

the granular particles preferably consist of NaCl, sugars, CaSO_4 , β -TCP, polylactides, polyglycolides or polylactide/polyglycolide copolymer, CaCO_3 CaHPO_4 .

[0041] The preparations of the present invention can be used, e.g., for medical purposes, for tooth cement and for bone replacement or bone filler or bone cement or bone adhesive.

DETAILED DESCRIPTION OF THE INVENTION

[0042] The problems in the state of the art are preferably solved by the present invention to the effect that it is possible to set the ability for expansion of the hardening cement paste by variation in the admixture of strontium salts. In tests, as shown in the examples, it is namely shown that the ability for expansion of the cement mixture, the main phase of which is the magnesium ammonium phosphate in the hardened state, decreases with increasing weight portion of strontium salts in the total powder mixture. Consequently, with this invention a material for endodontology may be provided, which also has an expandable property in addition to adequate mechanically loadable stability.

- An object of this invention is to provide a material for bone replacement, for bone augmentation and bone regeneration, which may be resorbed in a limited time and the resistance to pressure of which may decrease adapted to the regeneration requirements of the body.

- Another object of the invention to provide a material that may be created, prepared and modeled under normal temperature conditions, preferably body temperature, in other words a cement.

[0043] It is characteristic of the material provided, that it may additionally be adjusted by the intensity of the degree of sintering of the $\text{Mg}_3(\text{PO}_4)_2$ introduced in its processing time, in particular at room temperature, wherein the rate of solubility on the surface of these particles is controlled by the degree of sintering and the density of the $\text{Mg}_3(\text{PO}_4)_2$ used resulting therefrom, so that the precipitation of the Ca/Mg/phosphate compound settling out necessary for solidification may be controlled.

[0044] Furthermore, it is the object of this invention to provide a phosphate cement having partial solubility, preferably due to the slow solubility of the magnesium ammonium phosphate apatite structure (cement).

[0045] Furthermore, it is the object of the present invention to describe a reaction process, which leads to the formation of a magnesium ammonium phosphate cement from a number of individual components and which hardens in a clinically acceptable time at room and/or body temperature.

[0046] Furthermore, it is the object of the present invention to provide a material which becomes adequately hard and stable in a clinically acceptable time and which has a strong ability for adhesion to mineralized surfaces.

[0047] Furthermore, the object of the invention is the material disclosed according to the invention which is characterized by a strong ability for adhesion to metallic surfaces.

[0048] Furthermore, it is the object of the present invention to provide a resorbable cement, which can be injected in the form of a mixed paste.

[0049] One aspect of this invention is that the end product consists of a powder mixture having a molar Ca/P ratio in the range from 1.00 to 1.50. (P represents orthophosphate).

[0050] In addition, it is essential that the molar ratio Mg/P ratio of this powder mixture includes the range from 0 to 1.00.

[0051] In order to mix and to shape a cement paste, which hardens within an acceptable time, these powder mixtures must be adequately reactive. In order to achieve this, a further aspect of this invention is to mix the powder mixtures with suitable quantities of slightly basic ($7 < \text{pH} < 12$), aqueous solutions of soluble ionic constituents, such as for example: Na_3PO_4 , K_2CO_3 and/or Na_2CO_3 in combination with $(\text{NH}_4)_2\text{HPO}_4$.

[0052] A further feature of this invention is that granular but granular solids which are thus slightly soluble in the bodily fluid are admixed to the hardening cement paste, so that after settling-out thereof, a microporous to macroporous pore system results.

[0053] A further aspect of this invention is that these cements reach their maximum solidity within a few hours.

[0054] A further feature of this invention lies in the ability for expansion of the cement during setting. The expansivity is determined or adjusted by the relative proportion of an admixed strontium salt.

5 [0055] A further feature of this invention is that the hardened cement consists of microcrystalline magnesium ammonium phosphate.

[0056] A further feature of this invention is that the initial hardening time of the cement may be set at 1 to 40 minutes and the final hardening time at 2.5 to 60 minutes. (according to ASTM C266-89)

10 [0057] A further feature of this invention is that the cement may reach a maximum compressive strength of over 50 MPa.

[0058] A further feature of this invention is that the cement paste can be injected before reaching the initial hardening time.

15 [0059] A further feature of this invention is that the cement paste may serve as excipient for other materials which are not Ca, Mg and/or phosphate. For example ZnO, pharmaceutical active ingredients (antibiotics, cytostatic agents, growth factors) or other bioactive substances.

[0060] Further features and advantages of the invention can be seen from the description of exemplary embodiments.

Examples:

20 The following symbols are used in the examples:

P = powder mixture

L = liquid

UP = liquid/powder ratio in ml/g

t_i = initial hardening time (according to ASTM standard C266-89, Gilmoore needle)

25 t_F = final (end) hardening time (according to ASTM standard C266-89, Gilmoore needle)

$D(x\text{ h})$ = compressive strength in Mpa after x hours storage in 0.9% strength NaCl solution at 37°C

30 Production: After weighing out all constituents, the powder mixture is homogenized in a ball mill for about 20 minutes.

Example 1:

P=	60 g α -Ca ₃ (PO ₄) ₂ +6 g MgHPO ₄ •3H ₂ O+5 g MgSO ₄ •7H ₂ O		
L=	2M (NH ₄) ₂ HPO ₄	L/P=	0.40
t _i =	9	T _F =	21
D(18)	18.4 ± 1.5		
D(72)	26.1 ± 4.0		

Example 2:

P=	60 g α -Ca ₃ (PO ₄) ₂ +14 g MgHPO ₄ •3H ₂ O+2 g Mg(OH) ₂		
L=	3.5 M (NH ₄) ₂ HPO ₄	L/P=	0.35
t _i =	3	T _F =	7
D(18)	32.5 ± 3.5		
D(72)	46.9 ± 5.4		

5 Example 3:

P=	60 g α -Ca ₃ (PO ₄) ₂ +16 g MgHPO ₄ •3H ₂ O+3 g Na(PO ₄) ₃ •12H ₂ O		
L=	3.5 M (NH ₄) ₂ HPO ₄	L/P=	0.35
t _i =	6	T _F =	14
D(18)	44.7 ± 3.4		
D(72)	51.7 ± 5.0		

Example 4:

P=	60 g α -Ca ₃ (PO ₄) ₂ +14 g MgHPO ₄ •3H ₂ O+2 g ZnO		
L=	3.5 M (NH ₄) ₂ HPO ₄	L/P=	0.35
t _i =	6	T _F =	23
D(18)	35.1 ± 5.3		
D(72)	42.9 ± 0.8		

Example 5:

P=	45 g CaHPO ₄ •2 H ₂ O + 14 g MgHPO ₄ •3H ₂ O+6 g Mg(OH) ₂		
L=	2 M (NH ₄) ₂ HPO ₄	L/P=	0.40
t _i =	2.5	T _F =	7.5
D(18)	3.8 ± 1.2		

Example 6:

P=	45 g $\text{CaHPO}_4 \cdot 2 \text{H}_2\text{O}$ + 14 g CaCO_3 + 14 g $\text{MgHPO}_4 \cdot 3\text{H}_2\text{O}$ + 6 g ZnO		
L=	3.5 M $(\text{NH}_4)_2\text{HPO}_4$	L/P=	0.35
t_i =	2	T_F =	4
D(18)	3.8 ± 1.2		

Example 7:

P=	60 g $\alpha\text{-Ca}_3(\text{PO}_4)_2$ + 16 g $\text{MgHPO}_4 \cdot 3\text{H}_2\text{O}$ + 5 g $\beta\text{-Ca}_3(\text{PO}_4)_2$		
L=	3.5 M $(\text{NH}_4)_2\text{HPO}_4$	L/P=	0.35
t_i =	4	T_F =	9
D(2)	59.3 ± 1.0		
D(4)	55.6 ± 5.0		
D(18)	61.6 ± 5.0		
D(72)	51.5 ± 6.6		
D(18d)	28.1 ± 4.6		

5 **Example 8:**

P=	60 g $\alpha\text{-Ca}_3(\text{PO}_4)_2$ + 16 g $\text{MgHPO}_4 \cdot 3\text{H}_2\text{O}$ + 5 g $\beta\text{-Ca}_3(\text{PO}_4)_2$		
L=	3.5 M $(\text{NH}_4)_2\text{HPO}_4$	L/P=	0.35
t_i =	3.5	T_F =	11.5
D(2)	54.4 ± 3.3		
D(18)	65.6 ± 5.3		
D(4d)	56.6 ± 8.6		
D(18d)	36.3 ± 2.4		
D(30d)	30.0 ± 3.0		

Example 9:

P=	60 g $\alpha\text{-Ca}_3(\text{PO}_4)_2$ + 16 g $\text{MgHPO}_4 \cdot 3\text{H}_2\text{O}$ + 5 g $\beta\text{-Ca}_3(\text{PO}_4)_2$ + 0.8 g SrCO_3		
L=	3.5 M $(\text{NH}_4)_2\text{HPO}_4$	L/P=	0.35
t_i =	5.5	T_F =	13
D(2.5)	54.3 ± 4.6		
D(5)	61.1 ± 5.5		
D(18)	70.1 ± 5.7		
D(4d)	74.3 ± 9.3		
D(18d)	43.4 ± 3.4		
D(30d)	34.0 ± 4.0		

Example 10:

P=	60 g α -Ca ₃ (PO ₄) ₂ + 8 g MgHPO ₄ • 3H ₂ O + 2 g (NH ₄) ₂ SO ₄ + 2 g KH ₂ PO ₄ + 3.5 g SrCO ₃		
L=	3.5 M (NH ₄) ₂ HPO ₄	L/P=	0.30
t _i =		T _F =	
D(0.25)	11.2 ± 0.8		
D(0.5)	17.2 ± 1.8		
D(2)	31.7 ± 1.3		
D(6)	39.7 ± 0.63		
D(3d)	56.5 ± 4.9		

Example 11:

P=	60 g α -Ca ₃ (PO ₄) ₂ + 8 g MgHPO ₄ • 3H ₂ O + 4 g (NH ₄)H ₂ PO ₄ + 1 g SrCO ₃		
L=	3.5 M (NH ₄) ₂ HPO ₄	L/P=	0.37
t _i =		T _F =	
D(2)	22.6 ± 1.0		
D(6)	31.4 ± 1.1		
D(18)	45.8 ± 1.8		
D(3d)	45.7 ± 2.9		
D(35d)	11.5 ± 1.2		

5 Example 12:

P=	60 g α -Ca ₃ (PO ₄) ₂ + 17.4 g MgHPO ₄ • 3H ₂ O + 7 g (NH ₄) ₂ SO ₄ + 1.7 g SrCO ₃		
L=	3.5 M (NH ₄) ₂ HPO ₄	L/P=	0.35
t _i =		T _F =	
D(2)	43.3 ± 2.9		
D(6)	45.4 ± 4.4		
D(18)	45.8 ± 1.8		
D(3d)	45.7 ± 2.9		
D(28d)	19.5 ± 5.1		

Example 13:

P=	60 g α -Ca ₃ (PO ₄) ₂ + 20 g CaHPO ₄ + 8 g CaCO ₃ + 1 g MgHPO ₄ + 1.7 g SrCO ₃		
L=	3.5 M (NH ₄) ₂ HPO ₄	L/P=	0.35
t _i =	2.5	T _F =	8
D(2)	43.3 ± 2.9		
D(6)	49.4 ± 3.7		
D(18)	54.3 ± 2.5		
D(3d)	53.6 ± 3.1		
D(28d)	54.5 ± 1.9		

Example 14:

P=	60 g β -Ca ₃ (PO ₄) ₂ + 17.4 g MgHPO ₄ · 3H ₂ O + 1.7 g SrCO ₃		
L=	3.5 M (NH ₄) ₂ HPO ₄	L/P=	0.35
t _i =	3.5	T _F =	9

5 Example 15:

P=	60 g α -TCP + 34.8 g MgHPO ₄ x 3H ₂ O + 13.2 g (NH ₄)SO ₄		
L=	5% NaHCO ₃	L/P=	0.35
t _i =	3	T _F =	10

Example 16:

P=	60 g α -TCP + 16 g MgHPO ₄ x 3H ₂ O + 5 g β -TCP + 20 g NaCL (diameter 150 μ m)		
L=	3.5 M (NH ₄) ₂ HPO ₄	L/P=	0.35
t _i =	5	T _F =	12

Example 17:

10 P = 60 g α -TCP + 6 g Mg₃(PO₄)₂ + 10 g KH₂PO₄ + 5 g β -TCP

Mixing solution: 3.2 molar solution (NH₄)₂HPO₄

L/P = 0.35

T_i = 10.8 t_f = 20

D(2) - 18.5 ± 1.0

15 D(18) = 48.3 ± 1.8

While the above is a complete description of the preferred embodiments of the invention, various alternatives, modifications, and equivalents may be used. Therefore, the above description should not be taken as limiting the scope of the invention which is defined by the appended claims.